

Classifications

EN 14700	DIN 8555	Material-No.
S Z Fe5	WSG 3-GZ-350-T	1.6356

Characteristics and field of use

UTP A 702 is used for repair, preventive maintenance and production of highly stressed cold and hot working tools, such as punching dies, cold and hot cutting knives, Al-die cast moulds, cold forging dies, drawing-, stamping- and chamfering tools. The weld deposit is, in as-welded condition, machinable and the subsequent artificial aging optimises the resistance to hot wear and alternating temperatures.

The weld deposit of UTP A 702 has high strength and good toughness.

Hardness of the pure weld deposit:

untreated 32 – 35 HRC

hot-aged 3 – 4 h / 480°C : 50 – 54 HRC

Typical analysis in %

C	Mo	Ni	Co	Ti	Al	Fe
0.02	4.0	18.0	12.0	1.6	0.1	balance

Welding instruction

Machine welding area to metallic bright finish. Preheat massive pieces to 100 – 150°C, on low-alloyed base metal apply min. 3 – 4 layers. Weld with lowest possible heat input.

Wire diameter [mm]	Current type	Shielding gas (EN ISO 14175)
1.2 x 1000*	DC (-)	I 1
1.6 x 1000	DC (-)	I 1
2.0 x 1000	DC (-)	I 1
2.4 x 1000	DC (-)	I 1
3.2 x 1000	DC (-)	I 1

*available on request